

CEMENT AND CONCRETE REFERENCE LABORATORY
PROFICIENCY SAMPLE PROGRAM

Final Report
C270 Masonry Mortar Proficiency Samples
Number 17 and Number 18

November 2003

CEMENT AND CONCRETE REFERENCE LABORATORY

AT THE
NATIONAL INSTITUTE OF STANDARDS AND TECHNOLOGY
GAITHERSBURG, MARYLAND 20899
(301) 975-6704

SPONSORED BY
COMMITTEE C-1 ON CEMENT
COMMITTEE C-9 ON CONCRETE AND
CONCRETE AGGREGATES
AMERICAN SOCIETY FOR TESTING AND MATERIALS

100 Bureau Dr., Stop 8618
Fax: 301-975-2243
e-mail: ccrl@nist.gov

November 21, 2003

TO: Participants in the CCRL C270 Masonry Mortar Proficiency Sample Program

SUBJECT: Final Report on C270 Masonry Mortar Proficiency Samples No. 17 and No. 18


Enclosed is your copy of the final report on the test results for the pair of CCRL **C270 Masonry Mortar Proficiency Samples** which were distributed in September 2003

This report consists of Table of Results for individual laboratory data, a statistical Summary of results, a set of general scatter diagrams, and associated detailed information.

The CCRL Proficiency Sample Programs are intended for internal use by the laboratory as a tool to identify potential problems in laboratory procedures or test equipment and to initiate remedial actions. These programs are designed to complement the CCRL Laboratory Inspection Program as part of a total quality system. Care should be taken when using this program for any other use.

It is presently anticipated that the next Masonry Mortar Proficiency Samples will be distributed in September 2004.

Sincerely,



Robin K. Haupt, Supervisor
CCRL Proficiency Sample Programs

Enclosure

TO: Participants in the CCRL C270 Masonry Mortar Proficiency Sample Program

FROM: Robin K. Haupt, Supervisor, PSP

SUBJECT: Explanation of Final Report on Results of Tests on C270 Masonry Mortar Proficiency Samples No. 17 and No. 18

This letter, and the material included with it, constitute the final report, and summary of results for the current pair of Masonry Mortar Proficiency Samples, which were distributed in September 2003. The material includes: a Table of Results for Individual laboratory data, a statistical Summary of Results, and a set of general Scatter Diagrams. Your laboratory number is shown at the top of the Individual Table of Results.

An explanation of the program is contained in the paper: "Statistical Evaluation of Interlaboratory Cement Tests" by J. R. Crandall and R. L. Blaine, and "Statistical Aspects of the Cement Testing Program" by W.J. Youden, which can be found in Volume 59, Proceedings of the 62nd Annual Meeting of the Society, June 25, 1959, American Society for Testing and Materials.

Laboratory Ratings

Each laboratory receives an individualized Table of Results. The Table of Results shows the test title and the reporting unit in the first two columns. After that it lists the laboratory's results for the odd and even numbered samples, overall averages for the odd and even numbered samples, and the laboratory's ratings for the odd and even samples.

The ratings for the individual laboratory were determined in the manner described by Crandall and Blaine using a rating scale of 1 to 5 instead of 0 to 4. The ratings have no valid standing beyond showing the difference between the individual laboratory result and the average for a particular test.

The following table details the relationship between the ratings and the averages.

Ratings	Range (Number of Standard Deviations)	Number (Per 100) of Laboratories achieving the rating ¹
5	Less than 1	69
4	1 to 1.5	18
3	1.5 to 2	9
2	2 to 2.5	3
1	Greater than 2.5	1

The sign of the rating merely shows whether the result reported was greater or less than the average obtained.

¹Youden, W.J., "Statistical Aspects of the Cement Testing Program", Volume 59, *Proceedings of the 62nd Annual Meeting of the Society, June 25, 1959, American Society for Testing and Materials.*

In cases where some laboratories' results are eliminated, averages, standard deviations, coefficients of variation, and the ratings of the other laboratories' results, are recalculated using the data remaining after the elimination. Since the laboratory ratings given are the results from this one series of tests, you need not attach too much significance to a single low rating, or pair of ratings, from this one series. A continuing tendency to get low ratings on several pairs of samples should lead a laboratory to consider the types of error, systematic and random, contribute to ratings that are low. Systematic error, which is indicated by low ratings with the same signs on each pair of samples, means a consistent error is occurring in equipment and/or test procedures. One indication of random error is low ratings on both samples with different signs. Since systematic error occurs with more regularity, its cause is generally easier to find than the cause of random error.

Summary of Results

Usually, averages, standard deviations, and coefficients of variation are given with all results reported, and then with one or more outlying results omitted. Sometimes, two or more recalculations with laboratories omitted, have been done for the same test. In these cases, all of the laboratories omitted in previous recalculations are also omitted in subsequent ones. Results omitted are values that are more than three standard deviations from the mean of one or both samples. Often, elimination of these outlying results has little effect on the average, but may have a more pronounced effect on the standard deviation and coefficient of variation.

Scatter Diagrams

General scatter diagrams are supplied with this report. Crandall and Blaine describe the manner of preparing scatter diagrams, and their interpretation, in the paper published in the 1959 ASTM Proceedings. Each laboratory will receive a complete set of diagrams according to their participation in the program.

Using the results received from each laboratory, a scatter diagram is generated for each test method by plotting the value for the odd numbered samples on the X, or horizontal axis, against the value for the even numbered samples on the Y, or vertical axis. To find your point, just plot as you would when plotting any scatter diagram. Vertical and horizontal dashed lines, which divide the diagrams into four sections or quadrants, place the average values for the odd and even numbered samples, respectively. The first line of print under the diagram includes the test number, as given on the data sheet, the test title, and the number of data points on the diagrams. The number of plotted points may not agree with the total number of data pairs included in the analysis because a few points may be off the diagram, and some points may represent several data pairs, which are identical. Laboratories whose points are off the diagram will have a rating of ± 1 for that particular test.

As described in Crandall and Blaine, a tight circular pattern of points around the intersection of the median lines is the ideal situation. Stretching out of the pattern into the first (upper right) and third (lower left) quadrants, suggests some kind of bias, or tendency for laboratories to get high or low results on both samples. Examination of the scatter diagrams may indicate strong evidence of bias in many cases.

CCRL PROFICIENCY SAMPLE PROGRAM
 C270 Masonry Mortar Proficiency Samples No. 17 and No. 18
 Final Report - November 21, 2003


SUMMARY OF RESULTS

Test	#Labs	Sample No. 17			Sample No. 18			
		Average	S.D.	C.V.	Average	S.D.	C.V.	
AIR CONTENT								
Air Content	prcnt	27	12.6	2.1	16.4	12.0	1.5	12.8
AC Mix Water	prcnt	27	61.8	5.9	9.59	60.3	5.2	8.58
AC Mix Water	prcnt *	26	60.8	3.6	5.86	59.6	4.0	6.73
AC Flow	prcnt	27	107	6.3	5.90	105	19.8	18.91
AC Flow	prcnt *	24	109	2.9	2.64	110	2.9	2.64
COMPRESSIVE STRENGTH								
Comp Str 7 day	psi	26	1760	1320.7	75.0	1726	744.3	43.1
Comp Str 7 day	psi *	25	1505	253.0	16.8	1589	262.5	16.5
Comp Str 28 day	psi	27	1853	315.8	17.0	1992	365.7	18.4
CS Mix Water	prcnt	25	61.8	3.9	6.39	60.3	4.5	7.52
CS Flow	prcnt	26	109	2.8	2.52	110	2.6	2.33
WATER RETENTION								
WR Mix Water	prcnt	21	60.7	3.7	6.07	59.5	4.1	6.85
WR Initial Flow	prcnt	21	109	3.6	3.30	111	3.4	3.10
WR Initial Flow	prcnt	20	109	3.7	3.37	111	3.3	3.02
WR Final Flow	prcnt	21	91	6.6	7.25	95	6.5	6.86
Water Retention	prcnt	21	84	4.6	5.54	85	5.0	5.90

* ELIMINATED LABS: Data over three S.D. from the mean

AC Mix Water 1097
 AC Flow 928 1097 1773
 Comp Str 7 day 1577
 WR Initial Flow 40

CCRL PROFICIENCY SAMPLE PROGRAM
Air Content
C270 MASONRY MORTAR SAMPLES NO. 17 & NO. 18



TEST NO.170


Air Content

27 POINTS

SAMPLE NO. 17 AVE 12.63 S.D. 2.1 C.V. 16.4

SAMPLE NO. 18 AVE 11.96 S.D. 1.5 C.V. 12.8

CCRL PROFICIENCY SAMPLE PROGRAM
Air Content - Water
C270 MASONRY MORTAR SAMPLES NO. 17 & NO. 18




TEST NO.180 Air Content - Mix Water 26 POINTS

SAMPLE NO. 17 AVE 60.85 S.D. 3.6 C.V. 5.86

SAMPLE NO. 18 AVE 59.64 S.D. 4.0 C.V. 6.73

LABS ELIMINATED 1097

CCRL PROFICIENCY SAMPLE PROGRAM
Air Content - Flow
C270 MASONRY MORTAR SAMPLES NO. 17 & NO. 18



TEST NO.190

Air Content - Flow


24 POINTS

SAMPLE NO. 17 AVE 108.92 S.D. 2.9 C.V. 2.64

SAMPLE NO. 18 AVE 110.29 S.D. 2.9 C.V. 2.64

LABS ELIMINATED 928 1097 1773

CCRL PROFICIENCY SAMPLE PROGRAM
Compressive Strength - 7 day
C270 MASONRY MORTAR SAMPLES NO. 17 & NO. 18




TEST NO.210 Compressive Strength - 7 day 25 POINTS

SAMPLE NO. 17 AVE 1505.2 S.D. 253.0 C.V. 16.8

SAMPLE NO. 18 AVE 1588.6 S.D. 262.5 C.V. 16.5

LABS ELIMINATED 1577

CCRL PROFICIENCY SAMPLE PROGRAM
Compressive Strength - 28 day
C270 MASONRY MORTAR SAMPLES NO. 17 & NO. 18




TEST NO.211 Compressive Strength - 28 day 27 POINTS

SAMPLE NO. 17 AVE 1852.6 S.D. 315.8 C.V. 17.0

SAMPLE NO. 18 AVE 1992.2 S.D. 365.7 C.V. 18.4


CCRL PROFICIENCY SAMPLE PROGRAM
Compressive Strength - Mix Water
C270 MASONRY MORTAR SAMPLES NO. 17 & NO. 18



TEST NO.220 Compressive Strength - Mix Water 25 POINTS

SAMPLE NO. 17	AVE	61.76	S.D.	3.9	C.V.	6.39
SAMPLE NO. 18	AVE	60.28	S.D.	4.5	C.V.	7.52

CCRL PROFICIENCY SAMPLE PROGRAM
Compressive Strength - Flow
C270 MASONRY MORTAR SAMPLES NO. 17 & NO. 18




TEST NO.230 Compressive Strength - Flow 26 POINTS

SAMPLE NO. 17 AVE 109.19 S.D. 2.8 C.V. 2.52

SAMPLE NO. 18 AVE 110.15 S.D. 2.6 C.V. 2.33

CCRL PROFICIENCY SAMPLE PROGRAM
Water Retention - Water
C270 MASONRY MORTAR SAMPLES NO. 17 & NO. 18




TEST NO.330 Water Retention - Mix Water 21 POINTS

SAMPLE NO. 17 AVE 60.70 S.D. 3.7 C.V. 6.07

SAMPLE NO. 18 AVE 59.50 S.D. 4.1 C.V. 6.85


CCRL PROFICIENCY SAMPLE PROGRAM
Water Retention - Final Flow
C270 MASONRY MORTAR SAMPLES NO. 17 & NO. 18



TEST NO.332 Water Retention - Final Flow 21 POINTS

SAMPLE NO. 17 AVE 91.2 S.D. 6.6 C.V. 7.25
SAMPLE NO. 18 AVE 94.7 S.D. 6.5 C.V. 6.86

CCRL PROFICIENCY SAMPLE PROGRAM
Water Retention Value
C270 MASONRY MORTAR SAMPLES NO. 17 & NO. 18



TEST NO.333

Water Retention

21 POINTS

SAMPLE NO. 17	AVE	83.8	S.D.	4.6	C.V.	5.54
SAMPLE NO. 18	AVE	85.2	S.D.	5.0	C.V.	5.90